





TEST REPORT

Test Report # 19H-003101 Date of Report Issue: May 15, 2019

Date of Sample Received: May 6, 2019 Pages: Page 1 of 31

CLIENT INFORMATION:

Company: Inkcups Now

Recipient: Joe

Recipient Email: Joes@inkcups.com

SAMPLE INFORMATION:

Description: SI-HD Series: SI-HD 110 lemon yellow, SI-HD 111 medium yellow, SI-HD 115

orange, SI-HD 121 signal red, SI-HD 122 carmin red, SI-HD 130 light blue, SI-HD 132 ultra blue, SI-HD 136 violet, SI-HD 140 bright green, SI-HD 160 white, SI-HD

Tested Age Grade:

165 black

Assortment: - Purchase Order Number: -

SKU/style No.: - Toy Co./Agency: -

Factory/Supplier/Vendor: - Country of Origin: United States

Country of Distribution: - Labeled Age Grade: -

Quantity Submitted: 1 pc per style Recommended Age Grade: -

Testing Period: 05/06/2019 – 05/09/2019

05/10/2019 - 05/15/2019



recommended Age Grade: -

OVERALL RESULT:

PASS

Refer to page 2 for test result summary and appropriate notes.

QIMA Testing (HK) Limited



Loska Yeung Lok Ka
Assistant Manager, Chemical Laboratory

QIMA Testing (HK) Limited * 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, Hong Kong * Tel: (852)3185 8000. The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation. The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



Test Report #: 19H-003101 Page 2 of 31

TEST RESULTS SUMMARY:

At the request of the client, the following tests were conducted:

CONCLUSION	TEST(S) CONDUCTED
PASS	CPSIA Section 106 & ASTM F963-17 Toy Safety, Clause 4.3.5 Total Elements Screening in
1 755	Paint and Similar Surface Coatings
PASS	CPSIA Section 106 & ASTM F963-17 Toy Safety, Clause 4.3.5 Soluble Elements in Paints
17.55	and Similar Surface Coatings
PASS	ASTM F2923-14 Consumer Product Safety for Children's Jewelry, Clause 8 Total
	Elements Screening in Paint and Surface Coatings
PASS	ASTM F2923-14 Consumer Product Safety for Children's Jewelry, Clause 8 Soluble
	Elements in Paint and Surface Coatings
PASS	ASTM F2999-14 Adult Jewelry, Clause 5 & 7 Total Elements Screening in Paint and Surface Coatings
PASS	ASTM F2999-14 Adult Jewelry, Clause 7 Soluble Elements in Paint and Surface Coatings
PASS	ASTM F2999-14 Adult Jewelry, Clause 5 Total Lead in Paint and Surface Coatings
PASS	CPSIA Section 101 & 16 CFR 1303, Total Lead in Paints and Surface Coatings
PASS	Washington Revised Code Section 70.240.020, Cadmium in Paints and Surface Coatings of Children's Product*
PASS	The Illinois Lead Poisoning Prevention Act (LPPA) (410 ILCS 45/6), Total Lead in Paints and Surface Coatings of Children's Jewelry and Childcare Articles
PASS	Connecticut Public Act 10-113 (Substituted House Bill 5314), Total Cadmium Content in Children's Jewelry
PASS	Maryland Chapter 578 (House Bill 145), Total Cadmium in Children's Jewelry
PASS	Minnesota Chapter 347-S.F. No. 2510, Total Cadmium Screening in Children's Jewelry
PASS	California Proposition 65, Phthalates (DBP, BBP, DEHP, DINP, DIDP, DnHP)
PASS	16 CFR 1307 Prohibition of Children's Toys and Child Care Articles Containing Specified Phthalates (DBP, BBP, DEHP, DINP, DHEXP / DnHP, DCHP, DIBP, DPENP)
PASS	Washington Revised Code Section 70.240.020, Phthalates in Children's Product
PASS	Canadian Toys Regulations SOR/2011-17 as Amended, Item 23 – Total Elements Screening in Paints and Surface Coatings
PASS	Canadian Toys Regulations SOR/2011-17 as Amended, Item 23 – Leachable Elements in Paints and Surface Coatings
PASS	Canadian Toys Regulations SOR/2011-17 as Amended, Item 23 – Total Lead and Mercury in Paints and Surface Coatings
PASS	Canadian Surface Coating Materials Regulations SOR/2016-193, Total Lead and Mercury in Paints and Surface Coatings

QIMA Testing (HK) Limited * 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, Hong Kong * Tel: (852)3185 8000. The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation. The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



Test Report #: 19H-003101 Page 3 of 31

PASS	Mexican Environmental Health NOM-252-SSA1-2011, Total Elements Screening from Toys and School Supplies
PASS	Mexican Environmental Health NOM-252-SSA1-2011, Soluble Elements from Toys and School Supplies

QIMA Testing (HK) Limited * 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, Hong Kong * Tel: (852)3185 8000. The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation. The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



Test Report #: 19H-003101 Page 4 of 31

DETAILED RESULTS:

CPSIA Section 106 & ASTM F963-17 Toy Safety, Clause 4.3.5 Total Elements Screening in Paint and Similar Surface Coatings

Test Method: ASTM F963-17 Clause 8.3.1

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	4+5+6					Soluble
Test Item	Result	Result	Result	Result	Result	Limit
rest item	(ppm)	(ppm)	(ppm)	(ppm)	(ppm)	(ppm)
Total Antimony (Sb)	ND					60
Total Arsenic (As)	ND					25
Total Barium (Ba)	ND					1000
Total Cadmium (Cd)	ND					75
Total Chromium (Cr)	ND					60
Total Lead (Pb)	ND					90
Total Mercury (Hg)	ND					60
Total Selenium (Se)	ND					500
Conclusion	PASS					

Note:

ppm (Parts per million) = mg/kg (Milligrams per kilogram)

LT = Less than

ND = Not detected (Reporting Limit: Sb, As, Ba, Cd, Cr, Pb, Hg = 20ppm; Se = 50ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration.

Remark:

The total heavy metals screening results of Specimen No. 1, 2, 3, 7, 8, 9, 10 and 11 exceeded 80% of the soluble heavy metal limits, therefore separate soluble analyses were conducted.

QIMA Testing (HK) Limited • 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, Hong Kong • Tel: (852)3185 8000. The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation. The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



Test Report #: 19H-003101 Page 5 of 31

DETAILED RESULTS:

CPSIA Section 106 & ASTM F963-17 Toy Safety, Clause 4.3.5 Soluble Elements in Paints and Similar Surface Coatings

Test Method: ASTM F963-17 Clause 8.3.2

Analytical Method: Inductively Coupled Plasma-Mass Spectrometry

Specimen No.	1	2	3	7	8	Soluble
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Limit (ppm)
Soluble Antimony (Sb)	ND	ND	ND	ND	ND	60
Soluble Arsenic (As)	ND	ND	ND	ND	ND	25
Soluble Barium (Ba)	ND	ND	ND	ND	ND	1000
Soluble Cadmium (Cd)	ND	ND	ND	ND	ND	75
Soluble Chromium (Cr)	ND	ND	ND	ND	ND	60
Soluble Lead (Pb)	ND	ND	ND	ND	ND	90
Soluble Mercury (Hg)	ND	ND	ND	ND	ND	60
Soluble Selenium (Se)	ND	ND	ND	ND	ND	500
Conclusion	PASS	PASS	PASS	PASS	PASS	

Note:

ppm (Parts per million) = mg/kg (Milligrams per kilogram)

LT = Less than

ND = Not detected (Reporting Limit = 2 ppm)

QIMA Testing (HK) Limited * 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, Hong Kong * Tel: (852)3185 8000. The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation. The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



Test Report #: 19H-003101 Page 6 of 31

DETAILED RESULTS:

CPSIA Section 106 & ASTM F963-17 Toy Safety, Clause 4.3.5 Soluble Elements in Paints and Similar Surface Coatings

Test Method: ASTM F963-17 Clause 8.3.2

Analytical Method: Inductively Coupled Plasma-Mass Spectrometry

Specimen No.	9	10	11			Soluble
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Limit (ppm)
Soluble Antimony (Sb)	ND	ND	ND			60
Soluble Arsenic (As)	ND	ND	ND			25
Soluble Barium (Ba)	ND	ND	ND			1000
Soluble Cadmium (Cd)	ND	ND	ND			75
Soluble Chromium (Cr)	ND	ND	ND			60
Soluble Lead (Pb)	ND	ND	ND			90
Soluble Mercury (Hg)	ND	ND	ND			60
Soluble Selenium (Se)	ND	ND	ND			500
Conclusion	PASS	PASS	PASS			

Note:

ppm (Parts per million) = mg/kg (Milligrams per kilogram)

LT = Less than

ND = Not detected (Reporting Limit = 2 ppm)

QIMA Testing (HK) Limited * 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, Hong Kong * Tel: (852)3185 8000. The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation. The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



Test Report #: 19H-003101 Page 7 of 31

DETAILED RESULTS:

ASTM F2923-14 Consumer Product Safety for Children's Jewelry, Clause 8 Total Elements Screening in Paint and Surface Coatings

Test Method: ASTM F963-11 Clause 8.3.1

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	4+5+6					Soluble
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Limit (ppm)
Total Antimony (Sb)	ND					60
Total Arsenic (As)	ND					25
Total Barium (Ba)	ND					1000
Total Cadmium (Cd)	ND					75
Total Chromium (Cr)	ND					60
Total Mercury (Hg)	ND					60
Total Selenium (Se)	ND					500
Conclusion	PASS					

Note:

ppm (Parts per million) = mg/kg (Milligrams per kilogram)

LT = Less than

ND = Not detected (Reporting Limit: Sb, As, Ba, Cd, Cr, Hg = 20 ppm; Se = 50 ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration.

Remark:

The total heavy metals screening results of Specimen No. 1, 2, 3, 7, 8, 9, 10 and 11 exceeded 80% of the soluble heavy metal limits, therefore separate soluble analyses were conducted.

QIMA Testing (HK) Limited • 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, Hong Kong • Tel: (852)3185 8000. The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation. The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



Test Report #: 19H-003101 Page 8 of 31

DETAILED RESULTS:

ASTM F2923-14 Consumer Product Safety for Children's Jewelry, Clause 8 Soluble Elements in Paint and Surface Coatings

Test Method: ASTM F963-11 Clause 8.3.2

Analytical Method: Inductively Coupled Plasma-Mass Spectrometry

Specimen No.	1	2	3	7	8	Soluble
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Limit (ppm)
Soluble Antimony (Sb)	ND	ND	ND	ND	ND	60
Soluble Arsenic (As)	ND	ND	ND	ND	ND	25
Soluble Barium (Ba)	ND	ND	ND	ND	ND	1000
Soluble Cadmium (Cd)	ND	ND	ND	ND	ND	75
Soluble Chromium (Cr)	ND	ND	ND	ND	ND	60
Soluble Mercury (Hg)	ND	ND	ND	ND	ND	60
Soluble Selenium (Se)	ND	ND	ND	ND	ND	500
Conclusion	PASS	PASS	PASS	PASS	PASS	

Note:

ppm (Parts per million) = mg/kg (Milligrams per kilogram)

LT = Less than

ND = Not detected (Reporting Limit = 2 ppm)

QIMA Testing (HK) Limited * 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, Hong Kong * Tel: (852)3185 8000. The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation. The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



Test Report #: 19H-003101 Page 9 of 31

DETAILED RESULTS:

ASTM F2923-14 Consumer Product Safety for Children's Jewelry, Clause 8 Soluble Elements in Paint and Surface Coatings

Test Method: ASTM F963-11 Clause 8.3.2

Analytical Method: Inductively Coupled Plasma-Mass Spectrometry

Specimen No.	9	10	11			Soluble
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Limit (ppm)
Soluble Antimony (Sb)	ND	ND	ND			60
Soluble Arsenic (As)	ND	ND	ND			25
Soluble Barium (Ba)	ND	ND	ND			1000
Soluble Cadmium (Cd)	ND	ND	ND			75
Soluble Chromium (Cr)	ND	ND	ND			60
Soluble Mercury (Hg)	ND	ND	ND			60
Soluble Selenium (Se)	ND	ND	ND			500
Conclusion	PASS	PASS	PASS			

Note:

ppm (Parts per million) = mg/kg (Milligrams per kilogram)

LT = Less than

ND = Not detected (Reporting Limit = 2 ppm)

QIMA Testing (HK) Limited * 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, Hong Kong * Tel: (852)3185 8000. The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation. The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



Test Report #: 19H-003101 Page 10 of 31

DETAILED RESULTS:

ASTM F2999-14 Adult Jewelry, Clause 5 & 7 Total Elements Screening in Paint and Surface Coatings

Test Method: ASTM F963-11 Clause 8.3.1

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	4+5+6					Soluble
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Limit (ppm)
Total Antimony (Sb)	ND					60
Total Arsenic (As)	ND					25
Total Barium (Ba)	ND					1000
Total Cadmium (Cd)	ND					75
Total Chromium (Cr)	ND					60
Total Lead (Pb)	ND					600*
Total Mercury (Hg)	ND					60
Total Selenium (Se)	ND					500
Conclusion	PASS					

Note:

ppm (Parts per million) = mg/kg (Milligrams per kilogram)

LT = Less than

ND = Not detected (Reporting Limit: Sb, As, Ba, Cd, Cr, Pb, Hg = 20 ppm; Se = 50 ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration.

Remark:

*Total limit

The total heavy metals screening results of Specimen No. 1, 2, 3, 7, 8, 9, 10 and 11 exceeded 80% of the soluble heavy metal limits, therefore separate soluble analyses were conducted.

QIMA Testing (HK) Limited • 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, Hong Kong • Tel: (852)3185 8000. The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation. The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



Test Report #: 19H-003101 Page 11 of 31

DETAILED RESULTS:

ASTM F2999-14 Adult Jewelry, Clause 7 Soluble Elements in Paint and Surface Coatings

Test Method: ASTM F963-11 Clause 8.3.2

Analytical Method: Inductively Coupled Plasma-Mass Spectrometry

Specimen No.	1	2	3	7	8	Soluble
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Limit (ppm)
Soluble Antimony (Sb)	ND	ND	ND	ND	ND	60
Soluble Arsenic (As)	ND	ND	ND	ND	ND	25
Soluble Barium (Ba)	ND	ND	ND	ND	ND	1000
Soluble Cadmium (Cd)	ND	ND	ND	ND	ND	75
Soluble Chromium (Cr)	ND	ND	ND	ND	ND	60
Soluble Mercury (Hg)	ND	ND	ND	ND	ND	60
Soluble Selenium (Se)	ND	ND	ND	ND	ND	500
Conclusion	PASS	PASS	PASS	PASS	PASS	

Note:

ppm (Parts per million) = mg/kg (Milligrams per kilogram)

LT = Less than

ND = Not detected (Reporting Limit = 2 ppm)

QIMA Testing (HK) Limited * 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, Hong Kong * Tel: (852)3185 8000. The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation. The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



Test Report #: 19H-003101 Page 12 of 31

DETAILED RESULTS:

ASTM F2999-14 Adult Jewelry, Clause 7 Soluble Elements in Paint and Surface Coatings

Test Method: ASTM F963-11 Clause 8.3.2

Analytical Method: Inductively Coupled Plasma-Mass Spectrometry

Specimen No.	9	10	11			Soluble
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Limit (ppm)
Soluble Antimony (Sb)	ND	ND	ND			60
Soluble Arsenic (As)	ND	ND	ND			25
Soluble Barium (Ba)	ND	ND	ND			1000
Soluble Cadmium (Cd)	ND	ND	ND			75
Soluble Chromium (Cr)	ND	ND	ND			60
Soluble Mercury (Hg)	ND	ND	ND			60
Soluble Selenium (Se)	ND	ND	ND			500
Conclusion	PASS	PASS	PASS			

Note:

ppm (Parts per million) = mg/kg (Milligrams per kilogram)

LT = Less than

ND = Not detected (Reporting Limit = 2 ppm)

QIMA Testing (HK) Limited * 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, Hong Kong * Tel: (852)3185 8000. The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation. The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



Test Report #: 19H-003101 Page 13 of 31

DETAILED RESULTS:

ASTM F2999-14 Adult Jewelry, Clause 5 Total Lead in Paint and Surface Coatings

Test Method: CPSC-CH-E-1003-09.1

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	1+2+3	7+8+9	10+11			Soluble
Test Item	Result	Result	Result	Result	Result	Limit
rest item	(ppm)	(ppm)	(ppm)	(ppm)	(ppm)	(ppm)
Total Lead (Pb)	ND	ND	ND			600
Conclusion	PASS	PASS	PASS			

Note:

ppm (Parts per million) = mg/kg (Milligrams per kilogram)

LT = Less than

ND = Not detected (Reporting Limit: Sb, As, Ba, Cd, Cr, Pb, Hg = 20 ppm; Se = 50 ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration.



Test Report #: 19H-003101 Page 14 of 31

DETAILED RESULTS:

CPSIA Section 101 & 16 CFR 1303, Total Lead in Paints and Surface Coatings

Test Method: CPSC-CH-E-1003-09.1

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	1+2+3	4+5+6	7+8+9	10+11		Total
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Limit (ppm)
Total Lead (Pb)	ND	ND	ND	ND		90
Conclusion	PASS	PASS	PASS	PASS		

Note.

ppm (Parts per million) = mg/kg (Milligrams per kilogram)

LT = Less than

ND = Not detected (Reporting Limit = 20 ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration.

QIMA Testing (HK) Limited * 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, Hong Kong * Tel: (852)3185 8000. The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation. The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



Test Report #: 19H-003101 Page 15 of 31

DETAILED RESULTS:

Washington Revised Code Section 70.240.020, Cadmium in Paints and Surface Coatings of Children's Product

Test Method: CPSC-CH-E-1003-09.1 (Modified)#

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	1+2+3	4+5+6	7+8+9	10+11		Total
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Limit (ppm)
Total Cadmium (Cd)	ND	ND	ND	ND		40
Conclusion	PASS	PASS	PASS	PASS		

Note:

ppm (Parts per million) = mg/kg (Milligrams per kilogram)

LT = Less than

ND = Not detected (Reporting Limit = 20 ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration.

QIMA Testing (HK) Limited * 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, Hong Kong * Tel: (852)3185 8000. The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation. The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



Test Report #: 19H-003101 Page 16 of 31

DETAILED RESULTS:

The Illinois Lead Poisoning Prevention Act (LPPA) (410 ILCS 45/6), Total Lead in Paints and Surface Coatings of Children's Jewelry and Childcare Articles

Test Method: CPSC-CH-E1003-09.1

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	1+2+3	4+5+6	7+8+9	10+11		Total
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Limit (ppm)
Total Lead (Pb)	ND	ND	ND	ND		40
Conclusion	PASS	PASS	PASS	PASS		

Note:

ppm (Parts per million) = mg/kg (Milligrams per kilogram)

LT = Less than

ND = Not detected (Reporting Limit = 20 ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration.

QIMA Testing (HK) Limited * 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, Hong Kong * Tel: (852)3185 8000. The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation. The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



Test Report #: 19H-003101 Page 17 of 31

DETAILED RESULTS:

Connecticut Public Act 10-113 (Substituted House Bill 5314), Total Cadmium Content in Children's Jewelry

Test Method: ASTM F963-17 Clause 8.3.1

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	1+2+3	4+5+6	7+8+9	10+11		Total
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Limit (ppm)
Total Cadmium (Cd)	ND	ND	ND	ND		75
Conclusion	PASS	PASS	PASS	PASS		

Note:

ppm (Parts per million) = mg/kg (Milligrams per kilogram)

LT = Less than

ND = Not detected (Reporting Limit = 20 ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration.

QIMA Testing (HK) Limited * 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, Hong Kong * Tel: (852)3185 8000. The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation. The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



Test Report #: 19H-003101 Page 18 of 31

DETAILED RESULTS:

Maryland Chapter 578 (House Bill 145), Total Cadmium in Children's Jewelry

Test Method: ASTM F963-17 Clause 8.3.1

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	1+2+3	4+5+6	7+8+9	10+11		Total
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Limit (ppm)
Total Cadmium (Cd)	ND	ND	ND	ND		75
Conclusion	PASS	PASS	PASS	PASS		

Note:

ppm (Parts per million) = mg/kg (Milligrams per kilogram)

LT = Less than

ND = Not detected (Reporting Limit = 20 ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration.

QIMA Testing (HK) Limited • 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, Hong Kong • Tel: (852)3185 8000. The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation. The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



Test Report #: 19H-003101 Page 19 of 31

DETAILED RESULTS:

Minnesota Chapter 347-S.F. No. 2510, Total Cadmium Screening in Children's Jewelry

Test Method: ASTM F963-17 Clause 8.3.1

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	1+2+3	4+5+6	7+8+9	10+11		Soluble
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Limit (ppm)
Total Cadmium (Cd)	ND	ND	ND	ND		75
Conclusion	PASS	PASS	PASS	PASS		

Note:

ppm (Parts per million) = mg/kg (Milligrams per kilogram)

LT = Less than

ND = Not detected (Reporting Limit = 20 ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration.

Remark:

The total cadmium screening results did not exceed the soluble cadmium limit, therefore, further soluble analyses were not conducted.

QIMA Testing (HK) Limited * 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, Hong Kong * Tel: (852)3185 8000. The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation. The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



Test Report #: 19H-003101 Page 20 of 31

DETAILED RESULTS:

California Proposition 65, Phthalates (DBP, BBP, DEHP, DINP, DIDP, DnHP)

Test Method: CPSC-CH-C1001-09.4

Analytical Method: Gas Chromatography with Mass Spectrometry

Specimen N	Specimen No.		4+5+6	7+8+9	10+11	
Test Item	CAS No.	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Limit (mg/kg)
Dibutyl phthalate (DBP)	84-74-2	ND	ND	ND	ND	1000
Benzyl butyl phthalate (BBP)	85-68-7	ND	ND	ND	ND	1000
Di-(2-ethylhexyl) phthalate (DEHP)	117-81-7	ND	ND	ND	ND	1000
Diisononyl phthalate (DINP)	28553-12-0 68515-48-0	ND	ND	ND	ND	1000
Diisodecyl phthalate (DIDP)	26761-40-0 68515-49-1	ND	ND	ND	ND	1000
Di-n-hexyl phthalate (DnHP)	84-75-3	ND	ND	ND	ND	1000
	Conclusion	PASS	PASS	PASS	PASS	

Note:

mg/kg (Milligrams per kilogram) = ppm (Parts per million) = 0.0001 % m/m (Percent by mass) LT = Less than

ND = Not detected (Reporting Limit = 300 mg/kg)

Composite results are based on specimen of least mass resulting in highest potential concentration.

Remark:

The specification is quoted from client's requirement.

QIMA Testing (HK) Limited * 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, Hong Kong * Tel: (852)3185 8000. The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation. The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



Test Report #: 19H-003101 Page 21 of 31

DETAILED RESULTS:

16 CFR 1307 Prohibition of Children's Toys and Child Care Articles Containing Specified Phthalates (DBP, BBP, DEHP, DINP, DHEXP / DnHP, DCHP, DIBP, DPENP)

Test Method: CPSC-CH-C1001-09.4

Analytical Method: Gas Chromatography with Mass Spectrometry

Specimen N	0.	1+2+3	4+5+6	7+8+9	10+11	
Test Item	CAS No.	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Limit (mg/kg)
Dibutyl phthalate (DBP)	84-74-2	ND	ND	ND	ND	1000
Benzyl butyl phthalate (BBP)	85-68-7	ND	ND	ND	ND	1000
Di-(2-ethylhexyl) phthalate (DEHP)	117-81-7	ND	ND	ND	ND	1000
Diisononyl phthalate (DINP)	28553-12-0 68515-48-0	ND	ND	ND	ND	1000
Di-n-hexyl phthalate (DHEXP / DnHP)	84-75-3	ND	ND	ND	ND	1000
Dicyclohexyl phthalate (DCHP)	84-61-7	ND	ND	ND	ND	1000
Diisobutyl phthalate (DIBP)	84-69-5	ND	ND	ND	ND	1000
Di-n-pentyl phthalate (DPENP)	131-18-0	ND	ND	ND	ND	1000
	Conclusion	PASS	PASS	PASS	PASS	

Note.

mg/kg (Milligrams per kilogram) = ppm (Parts per million) = 0.0001 % m/m (Percent by mass)

LT = Less than

ND = Not detected (Reporting Limit = 300 mg/kg)

Composite results are based on specimen of least mass resulting in highest potential concentration.

QIMA Testing (HK) Limited • 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, Hong Kong • Tel: (852)3185 8000. The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation. The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



Test Report #: 19H-003101 Page 22 of 31

DETAILED RESULTS:

Washington Revised Code Section 70.240.020, Phthalates in Children's Product

Test Method: CPSC-CH-C1001-09.4

Analytical Method: Gas Chromatography with Mass Spectrometry

Specimen No	Specimen No.		4+5+6	7+8+9	10+11	
Test Item	CAS No.	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Limit (mg/kg)
Dibutyl phthalate (DBP)	84-74-2	ND	ND	ND	ND	1000
Benzyl butyl phthalate (BBP)	85-68-7	ND	ND	ND	ND	1000
Di-(2-ethylhexyl) phthalate (DEHP)	117-81-7	ND	ND	ND	ND	1000
Di-n-octyl phthalate (DnOP)	117-84-0	ND	ND	ND	ND	1000
Diisononyl phthalate (DINP)	28553-12-0 68515-48-0	ND	ND	ND	ND	1000
Diisodecyl phthalate (DIDP)	26761-40-0 68515-49-1	ND	ND	ND	ND	1000
	Sum	ND	ND	ND	ND	1000
	Conclusion	PASS	PASS	PASS	PASS	

Note:

mg/kg (Milligrams per kilogram) = ppm (Parts per million) = 0.0001 % m/m (Percent by mass)

LT = Less than

ND = Not detected (Reporting Limit = 300 mg/kg)

Composite results are based on specimen of least mass resulting in highest potential concentration.

QIMA Testing (HK) Limited • 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, Hong Kong • Tel: (852)3185 8000. The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation. The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



Test Report #: 19H-003101 Page 23 of 31

DETAILED RESULTS:

Canadian Toys Regulations SOR/2011-17 as Amended, Item 23 – Total Elements Screening in Paints and Surface Coatings

Test Method: ASTM F963-17 Clause 8.3.1

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	1+2+3	4+5+6	7+8+9			Leachable
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Limit (ppm)
Total Antimony (Sb)	ND	ND	ND			1000
Total Arsenic (As)	ND	ND	ND			1000
Total Barium (Ba)	920	ND	820			1000
Total Cadmium (Cd)	ND	ND	ND			1000
Total Lead (Pb)	ND	ND	ND			90*
Total Mercury (Hg)	ND	ND	ND			10*
Total Selenium (Se)	ND	ND	ND			1000
Conclusion	PASS	PASS	PASS			

Note:

ppm (Parts per million) = mg/kg (Milligrams per kilogram)

LT = Less than

ND = Not detected (Reporting Limit: Pb, Hg = 10 ppm; Sb, As, Ba, Cd, Se = 50 ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration.

Remark:

*Total limit

The result of total elements screening of Specimen No. 10 and 11 exceeded the limit of leachable soluble limits, therefore separate analyses of leachable elements were conducted.

QIMA Testing (HK) Limited • 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, Hong Kong • Tel: (852)3185 8000. The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation. The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



Test Report #: 19H-003101 Page 24 of 31

DETAILED RESULTS:

Canadian Toys Regulations SOR/2011-17 as Amended, Item 23 – Leachable Elements in Paints and Surface Coatings

Test Method: Health Canada Method C-03 (Effective 2014-02-20)
Analytical Method: Inductively Coupled Plasma-Mass Spectrometry

Specimen No.	10	11				Leachable
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Limit (ppm)
Leachable Antimony (Sb)	ND	ND				1000
Leachable Arsenic (As)	ND	ND				1000
Leachable Barium (Ba)	ND	ND				1000
Leachable Cadmium (Cd)	ND	ND				1000
Leachable Selenium (Se)	ND	ND				1000
Conclusion	PASS	PASS				

Note:

ppm (Parts per million) = mg/kg (Milligrams per kilogram)

LT = Less than

ND = Not detected (Reporting Limit = 50 ppm)

QIMA Testing (HK) Limited * 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, Hong Kong * Tel: (852)3185 8000. The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation. The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



Test Report #: 19H-003101 Page 25 of 31

DETAILED RESULTS:

Canadian Toys Regulations SOR/2011-17 as Amended, Item 23 – Total Lead and Mercury in Paints and Surface Coatings

Test Method: ASTM F963-17 Clause 8.3.1

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	10+11					Total
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Limit (ppm)
Total Lead (Pb)	ND					90
Total Mercury (Hg)	ND					10
Conclusion	PASS					

Note

ppm (Parts per million) = mg/kg (Milligrams per kilogram)

LT = Less than

ND = Not detected (Reporting Limit = 10 ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration.

QIMA Testing (HK) Limited * 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, Hong Kong * Tel: (852)3185 8000. The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation. The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



Test Report #: 19H-003101 Page 26 of 31

DETAILED RESULTS:

Canadian Surface Coating Materials Regulations SOR/2016-193, Total Lead and Mercury in Paints and Surface Coatings

Test Method: ASTM F963-17 Clause 8.3.1

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	1+2+3	4+5+6	7+8+9	10+11		Total
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Limit (ppm)
Total Lead (Pb)	ND	ND	ND	ND		90
Total Mercury (Hg)	ND	ND	ND	ND		10
Conclusion	PASS	PASS	PASS	PASS		

Note

ppm (Parts per million) = mg/kg (Milligrams per kilogram)

LT = Less than

ND = Not detected (Reporting Limit = 10 ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration.

QIMA Testing (HK) Limited * 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, Hong Kong * Tel: (852)3185 8000. The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation. The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



Test Report #: 19H-003101 Page 27 of 31

DETAILED RESULTS:

Mexican Environmental Health NOM-252-SSA1-2011, Total Elements Screening from Toys and School Supplies

Test Method: ASTM F963-17 Clause 8.3.1

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Toy Material except Modelling Clay

Specimen No.	4+5+6					Soluble
Test Item	Result	Result	Result	Result	Result	Limit
	(ppm)	(ppm)	(ppm)	(ppm)	(ppm)	(ppm)
Total Antimony (Sb)	ND					60
Total Arsenic (As)	ND					25
Total Barium (Ba)	ND					1000
Total Cadmium (Cd)	ND					75
Total Chromium (Cr)	ND					60
Total Lead (Pb)	ND					90
Total Mercury (Hg)	ND					60
Total Selenium (Se)	ND					500
Conclusion	PASS					

Note:

ppm (Parts per million) = mg/kg (Milligrams per kilogram)

LT = Less than

ND = Not detected (Reporting Limit: Sb, As, Ba, Cd, Cr, Pb, Hg = 20 ppm; Se = 50 ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration

Remark:

The total heavy metals screening results of Specimen No. 1, 2, 3, 7, 8, 9, 10 and 11 exceeded 80% of the soluble heavy metal limits, therefore separate soluble analyses were conducted.

QIMA Testing (HK) Limited • 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, Hong Kong • Tel: (852)3185 8000. The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation. The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



Test Report #: 19H-003101 Page 28 of 31

DETAILED RESULTS:

Mexican Environmental Health NOM-252-SSA1-2011, Soluble Elements from Toys and School Supplies

Test Method: NOM-252-SSA1-2011 Appendix A

Analytical Method: Inductively Coupled Plasma-Mass Spectrometry

Toy Material except Modelling Clay

Specimen No.	1	2	3	7	8	Soluble
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Limit (ppm)
Soluble Antimony (Sb)	ND	ND	ND	ND	ND	60
Soluble Arsenic (As)	ND	ND	ND	ND	ND	25
Soluble Barium (Ba)	ND	ND	ND	ND	ND	1000
Soluble Cadmium (Cd)	ND	ND	ND	ND	ND	75
Soluble Chromium (Cr)	ND	ND	ND	ND	ND	60
Soluble Lead (Pb)	ND	ND	ND	ND	ND	90
Soluble Mercury (Hg)	ND	ND	ND	ND	ND	60
Soluble Selenium (Se)	ND	ND	ND	ND	ND	500
Conclusion	PASS	PASS	PASS	PASS	PASS	

Note:

mg/kg = Milligrams per kilogram

LT = Less than

ND = Not detected (Reporting Limit = 2 mg/kg)

QIMA Testing (HK) Limited * 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, Hong Kong * Tel: (852)3185 8000. The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation. The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



Test Report #: 19H-003101 Page 29 of 31

DETAILED RESULTS:

Mexican Environmental Health NOM-252-SSA1-2011, Soluble Elements from Toys and School Supplies

Test Method: NOM-252-SSA1-2011 Appendix A

Analytical Method: Inductively Coupled Plasma-Mass Spectrometry

Toy Material except Modelling Clay

Specimen No.	9	10	11			Soluble
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Limit (ppm)
Soluble Antimony (Sb)	ND	ND	ND			60
Soluble Arsenic (As)	ND	ND	ND			25
Soluble Barium (Ba)	ND	ND	ND			1000
Soluble Cadmium (Cd)	ND	ND	ND			75
Soluble Chromium (Cr)	ND	ND	ND			60
Soluble Lead (Pb)	ND	ND	ND			90
Soluble Mercury (Hg)	ND	ND	ND			60
Soluble Selenium (Se)	ND	ND	ND			500
Conclusion	PASS	PASS	PASS			

Note:

mg/kg = Milligrams per kilogram

LT = Less than

ND = Not detected (Reporting Limit = 2 mg/kg)

QIMA Testing (HK) Limited * 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, Hong Kong * Tel: (852)3185 8000. The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation. The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



Test Report #: 19H-003101 Page 30 of 31

SPECIMEN DESCRIPTION:

Specimen No.	Specimen Description	Location
1	Yellow ink	SI-HD 110 lemon yellow
2	Dark yellow ink	SI-HD 111 medium yellow
3	Orange ink	SI-HD 115 orange
4	Red ink	SI-HD 121 signal red
5	Dark red ink	SI-HD 122 carmin red
6	Blue ink	SI-HD 130 light blue
7	Dark blue ink	SI-HD 132 ultra blue
8	Purple ink	SI-HD 136 violet
9	Green ink	SI-HD 140 bright green
10	White ink	SI-HD 160 white
11	Black ink	SI-HD 165 black



Test Report #: 19H-003101 Page 31 of 31

SAMPLE PHOTO:



-End Report-

QIMA Testing (HK) Limited * 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, Hong Kong * Tel: (852)3185 8000. The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation. The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.