

INKCUPS CORPORATION
310 ANDOVER STREET, Danvers, MA 01923, United States

The following sample(s) was/were submitted and identified on behalf of the client as:

Sample Description : (A) ONE SAMPLE OF ICN SB ECO SERIES INK IN 165 BLACK.

Buyer : PUMA
SGS Job No. : SL12200251709901TX
Application No. : /
Division : Apparel
Product Type : Others
Product Stage : /
Business Unit : /
Sample Type : Material
Puma Supplier No. : /
Material Reference Code : /
Colours code/ Prints : /
Season : AH2022
Article no. : /
Style No. : /
Fiber Composition : /
Oeko Tex certified product : /
Country of Origin : Italy
Country Of Destination : /
Supplier : /
Performance Code : /
Reference No : /
TRF# : 56307
Test Specification : V-4.2021
Test Package/ Material Type : Prints, Inks
Sourcing Office : Puma Global Sourcing – South Africa
Sample Status : Production
T2 Supplier : Ink Cups – Hong Kong
Supplier Material Name : ICN SB ECO SERIES INK – 165 Black
Previous report No : /

Test Performed : Selected test(s) as requested by applicant

Sample Receiving Date : Mar 22, 2022

Testing Period : Mar 22, 2022 - Mar 29, 2022

Test Result(s) : Unless otherwise stated the results shown in this test report refer only to the sample(s) tested, for further details, please refer to the following page(s).

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Conclusion	A
Alkylphenol Ethoxylates (APEO) and Alkylphenols(AP)	Pass
Disperse Dyes	Pass
O-phenylphenol (OPP)	Pass
pH Value	Pass
Azo Dyes	Pass
Vinyl Chloride Monomer(VCM)	Pass
Formaldehyde	Pass
Extractable Heavy Metal	Pass
Monomers - Styrene	Pass
Phthalates	Pass
Polyaromatic hydrocarbons Content (PAH)	Pass
Volatile Organic Compounds(VOC)	Pass
Total Arsenic Content	Pass
Total Cadmium Content	Pass
Total Mercury Content	Pass
Total Lead Content	Pass
N, N-dimethylformamide (DMFa)	Pass
Solvent Residue	Pass
Organotins	Pass
Perfluorinated Compounds (PFCs)	Pass

Remark(s) : Pass = Meet Puma's Requirement

Signed for and on behalf of
SGS (Hong Kong) Limited



Chan Kai Kong, Alfred, Assistant Technical Manager

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Sample Photo



This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

COMPONENT LIST / List of Materials

Sample No.	Component No.	Description	Material	Color	Remark
A	1	dried ink	Coatings & Prints	black	/

Test Result

Alkylphenols (AP) & Alkylphenol Ethoxylates (APEO)

Test Method : AP: With reference to AFIRM RSL 2022 method by solvent extraction. Analysis was conducted by HPLC-MS.

APEO: With reference to EN ISO 18254-1:2016. Analysis was conducted by HPLC-MS.

<u>Test Item(s)</u>	1
Nonylphenol(NP)	ND
Octylphenol(OP)	ND
Nonylphenol ethoxylates (NPEOs)	ND
Octylphenol ethoxylates (OPEOs)	ND
Sum of AP	ND
Sum of AP & APEO	ND
Conclusion	PASS

Notes :

Note: n.d. = Not Detected

mg/kg = ppm

* = Exceed the limit

= result over 1/2 or 1/3 of client requirement. There is a possibility of failure on one or more components. Retesting on individual component is recommended to determine the compliance of each component to the requirement.

Δ = result over 1/2 or 1/3 of client requirement. There is a possibility of failure on one or more components. Retesting on individual component has been carried out as requested to determine the compliance of each component to the requirement

Reporting limit = AP: 3 mg/kg; APEO: 20 mg/kg

Requirement:

Sum of AP 10 mg/kg

Sum of AP & APEO 100 mg/kg

Forbidden and Disperse Dyes

Test Method : With reference to DIN 54231:2005. Analysis was conducted with HPLC-DAD-MSD.

<u>Test Item(s)</u>	<u>CAS NO.</u>	<u>1</u>
Disperse Blue 1	2475-45-8	ND
Disperse Blue 3	2475-46-9	ND
Disperse Blue 7	3179-90-6	ND
Disperse Blue 26	3860-63-7	ND
Disperse Blue 35A	56524-77-7	ND
Disperse Blue 35B	56524-76-6	ND
Disperse Blue 102	69766-79-6/12222 -97-8	ND
Disperse Blue 106	68516-81-4/12223 -01-7	ND
Disperse Blue 124	61951-51-7	ND
Disperse Brown 1	23355-64-8	ND
Disperse Orange 1	2581-69-3	ND
Disperse Orange 3	730-40-5	ND
Disperse Orange 11	82-28-0	ND
Disperse Orange 37/59/76	n.a.	ND
Disperse Orange 149	85136-74-9	ND
Disperse Red 1	2872-52-8	ND
Disperse Red 11	2872-48-2	ND
Disperse Red 17	3179-89-3	ND
Disperse Red 151	61968-47-6	ND
Disperse Yellow 1	119-15-3	ND
Disperse Yellow 3	2832-40-8	ND
Disperse Yellow 7	6300-37-4	ND
Disperse Yellow 9	6373-73-5	ND
Disperse Yellow 23	6250-23-3	ND
Disperse Yellow 39	12236-29-2	ND
Disperse Yellow 49	54824-37-2	ND
Disperse Yellow 56	54077-16-6	ND
Acid Red 26	3761-53-3	ND
Basic Red 9	569-61-9	ND
Basic Green 4	569-64-2 / 2437-29-8 / 10309-95-2	ND
Basic Violet 3	548-62-9	ND

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Test Method : With reference to DIN 54231:2005. Analysis was conducted with HPLC-DAD-MSD.

<u>Test Item(s)</u>	<u>CAS NO.</u>	1
Basic Violet 14	632-99-5	ND
Basic Blue 26 (with Michler's Ketone > 0.1%)	2580-56-5	ND
Direct Black 38	1937-37-7	ND
Direct Blue 6	2602-46-2	ND
Direct Red 28	573-58-0	ND
Direct Brown 95	16071-86-6	ND
4-Dimethylaminoazobenzene (Solvent Yellow 2)	60-11-7	ND
Solvent Blue 4	6786-83-0	ND
4, 4'-bis (dimethylamino)-4-(methyl amino)trityl alcohol	561-41-1	ND
Conclusion		PASS

Notes :

Note: n.d. = not detected

mg/kg = ppm

* = Exceed the limit

+ = result was back calculated based on the worst-case scenario of Basic Green 4 cation (CAS 10309-95-2)

= result over 1/2 or 1/3 of client requirement. There is a possibility of failure on one or more components. Retesting on individual component is recommended to determine the compliance of each component to the requirement

Δ = result over 1/2 or 1/3 of client requirement. There is a possibility of failure on one or more components. Retesting on individual component has been carried out as requested to determine the compliance of each component to the requirement

Reporting limit = 10 mg/kg (each)

Requirement 30 mg/kg (each)

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Ortho-Phenyl Phenol Content

Test Method : With reference to DIN 50009:2021. Analysis was conducted by GC-MS.

<u>Test Item(s)</u>	1
Ortho-phenylphenol (OPP)	ND
Conclusion	PASS

Notes :

- Note: n.d.= Not detected
- mg/k = ppm
- * = Exceed the limit
- # = result over 1/2 or 1/3 of client requirement. There is a possibility of failure on one or more components. Retesting on individual component is recommended to determine the compliance of each component to the requirement
- Δ = result over 1/2 or 1/3 of client requirement. There is a possibility of failure on one or more components. Retesting on individual component has been carried out as requested to determine the compliance of each component to the requirement
- Reporting limit = 100 mg/kg

Requirement 1000 mg/kg

pH Value in Textile and Artificial Leather

Test Method : According to EN ISO 3071:2020.

<u>Test Item(s)</u>	1
pH value	5.8
Conclusion	PASS

Notes :

- Note: Extraction medium KCl solution
- pH value of extraction medium 5.0 - 7.5
- Temperature of the extraction solution 22 +/- 2 °C

Requirement: 4.0 - 7.5

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Azo Dyes and Arylamine Salts (Direct Reduction)

Test Method : Textile: With reference to EN ISO 14362-1:2017. Analysis was conducted by GC-MS/HPLC-DAD.
 Determination of 4-aminoazobenzene (CAS No.:60-09-3)-EN ISO 14362-3:2017; Analysis was conducted by GC-MS/ HPLC-DAD.

<u>Test Item(s)</u>	<u>CAS NO.</u>	1
4-Aminobiphenyl	92-67-1	ND
Benzidine	92-87-5	ND
4-chloro-o-toluidine	95-69-2	ND
2-naphthylamine	91-59-8	ND
o-aminoazotoluene	97-56-3	ND
5-nitro-o-toluidine / 2-Amino-4-nitrotoluene	99-55-8	ND
4-chloroaniline	106-47-8	ND
4-methoxy-m-phenylenediamine / 2,4-Diaminoanisole	615-05-4	ND
4,4'-Diaminodiphenylmethane (MDA)	101-77-9	ND
3,3'-dichlorobenzidine	91-94-1	ND
3,3'-dimethoxybenzidine	119-90-4	ND
3,3'-dimethylbenzidine	119-93-7	ND
3,3'-Dimethyl-4,4'-diaminodiphenylmethane / 4,4'-methylenedi-o-toluidine	838-88-0	ND
p-cresidine / 2-methoxy-5-methylaniline / 6-methoxy-m-toluidine	120-71-8	ND
4,4'-methylene-bis-(2-chloroaniline)	101-14-4	ND
4,4'-oxydianiline	101-80-4	ND
4,4'-thiodianiline	139-65-1	ND
o-toluidine	95-53-4	ND
4-methyl-m-phenylenediamine / 2,4-Toluyldiamine (TDA)	95-80-7	ND
2,4,5-trimethylaniline	137-17-7	ND
4-aminoazobenzene	60-09-3	ND
O-Anisidine	90-04-0	ND
2,4-Xylidine	95-68-1	ND
2,6-Xylidine	87-62-7	ND
4-chloro-o-toluidinium chloride+	3165-93-3	ND
2-Naphthylammoniumacetate+	553-00-4	ND
4-methoxy-m-phenylene diammonium sulphate; 2,4-diaminoanisole sulphate+	39156-41-7	ND
2,4,5-trimethylaniline hydrochloride+	21436-97-5	ND
Conclusion		PASS

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Notes :

Note: n.d. = not detected

mg/kg = ppm

* = Exceed the limit

= result over 1/2 or 1/3 of client requirement. There is a possibility of failure on one or more components. Retesting on individual component is recommended to determine the compliance of each component to the requirement.

Δ = result over 1/2 or 1/3 of client requirement. There is a possibility of failure on one or more components. Retesting on individual component has been carried out as requested to determine the

compliance of each component to the requirement

+ = Result was back calculated based on the determination of its amine

@ = The amine was detected according to EN ISO 14362-1:2017 with the reducing agent. A similar result was obtained from the procedure carried out without the reducing agent. According to EN ISO 14362-1:2017 Annex C.2.1.2.2, the amine originated from a source other than azo colorants.

^ = The amine was detected according to EN ISO 14362-1:2017 with the reducing agent. Confirmation procedure was carried out without reducing agent, according to EN ISO 14362-1:2017 Annex C.2.1.2.2, the amine originated from azo colorants.

Reporting limit = 5 mg/kg (each)

Requirement: 20 mg/kg (each)

Remark: + Direct reduction refers to the extraction and reduction according to EN ISO 14362-1:2017 clause 10.2 and relevant clauses.

4-Aminodiphenyl (CAS No. 92-67-1), 2-Naphthylamine (CAS No. 91-59-8) and 2,4-Diaminoanisole (CAS No. 615-05-4) can be indirectly generated from some colorants which do not contain these amines azo bound. The use of banned azo colorants cannot be reliably ascertained without additional information.

In case PU is used, e.g. PU Foams or coatings, it cannot be ruled out that MDA (CAS No. 101-77-9) and TDA (CAS No. 95-80-7) can be released from PU material, not from banned azo colorant. Similarly, for pigment prints, MDA will be released from a chemical fixing agent.

EN ISO 14362-1:2017 will enable further cleavage of 4-AAB (CAS No. 60-09-3) to non-forbidden amines: aniline and p-phenylenediamine. If aniline and/or p-phenylenediamine is not found, 4-AAB is considered as "n.d." (i.e. <5.0 mg/kg). Otherwise, EN ISO 14362-3:2017 will be employed to verify the presence of 4-AAB.

Monomer - Vinyl Chloride

Test Method : With reference to EN ISO 6401:2008. Analysis was conducted by headspace GC-MS.

<u>Test Item(s)</u>	1
vinyl chloride monomer(VCM)	ND
Conclusion	PASS

Notes :

- Note: n.d. = not detected
- mg/kg = ppm
- * = Exceed the limit
- # = result over 1/2 or 1/3 of client requirement. There is a possibility of failure on one or more components. Retesting on individual component is recommended to determine the compliance of each component to the requirement
- Δ = result over 1/2 or 1/3 of client requirement. There is a possibility of failure on one or more components. Retesting on individual component has been carried out as requested to determine the compliance of each component to the requirement
- Reporting limit: 0.3 mg/kg

- Requirement 1 mg/kg

Formaldehyde - All materials, except Leather

Test Method : With reference to EN ISO 14184-1:2011. Analysis was conducted by UV/VIS spectrophotometer.

<u>Test Item(s)</u>	<u>CAS NO.</u>	1
Formaldehyde	50-00-0	ND
Conclusion		PASS

Notes :

- Note: n.d. = Not detected
- mg/kg = ppm
- * = Exceed the limit
- # = result over 1/2 or 1/3 of client requirement. There is a possibility of failure on one or more components. Retesting on individual component is recommended to determine the compliance of each component to the requirement
- Δ = result over 1/2 or 1/3 of client requirement. There is a possibility of failure on one or more components. Retesting on individual component has been carried out as requested to determine the compliance of each component to the requirement
- Reporting limit = 5 mg/kg

- Requirement
- Babies 16 mg/kg
- Adults and Children 75 mg/kg

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Extractable Heavy Metal - All other materials

Test Method : With reference to DIN EN 16711-2:2016. Analysis was performed ICP-OES or ICP-MS.

<u>Test Item(s)</u>	<u>CAS NO.</u>	1
Antimony (Sb)	7440-36-0	ND
Arsenic (As)	7440-38-2	ND
Barium (Ba)	7440-39-3	ND
Cadmium (Cd)	7440-43-9	ND
Cobalt (Co)	7440-48-4	ND
Copper (Cu)	7440-50-8	ND
Lead (Pb)	7439-92-1	ND
Selenium (Se)	7782-49-2	ND
Mercury (Hg)	7439-97-6	ND
Nickel (Ni)	7440-02-0	ND
Conclusion		PASS

Notes :

Note: n.d. = Not detected

mg/kg = ppm

* = Exceed the limit

= result over 1/2 or 1/3 of client requirement. There is a possibility of failure on one or more components. Retesting on individual component is recommended to determine the compliance of each component to the requirement.

Δ = result over 1/2 or 1/3 of client requirement. There is a possibility of failure on one or more components. Retesting on individual component has been carried out as requested to determine the compliance of each component to the requirement

Requirement	<u>Reporting limit (mg/kg)</u>	<u>Babies (mg/kg)</u>	<u>Children (mg/kg)</u>	<u>Adults (mg/kg)</u>
Antimony (Sb)	3.0	30	30	30
Arsenic (As)	0.06	0.2	0.2	0.2
Barium (Ba)	100	1000	1000	1000
Cadmium (Cd)	0.03	0.1	0.1	0.1
Cobalt (Co)	0.3	1.0	1.0	4.0
Copper (Cu)	5.0	25	25	50
Lead (Pb)	0.06	0.2	1.0	1.0
Mercury (Hg)	0.006	0.02	0.02	0.02
Nickel (Ni)	0.1	1.0	1.0	1.0
Selenium (Se)	50	500	500	500

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Monomer - Free Styrene

Test Method : With reference to AFIRM RSL 2022 method by solvent extraction. Analysis was conducted by GC-MS.

<u>Test Item(s)</u>	<u>CAS NO.</u>	<u>1</u>
Styrene	100-42-5	ND
Conclusion		PASS

Notes :

Note: n.d. = not detected

mg/kg = ppm

* = Exceed the limit

= result over 1/2 or 1/3 of client requirement. There is a possibility of failure on one or more components. Retesting on individual component is recommended to determine the compliance of each component to the requirement

Δ = result over 1/2 or 1/3 of client requirement. There is a possibility of failure on one or more components. Retesting on individual component has been carried out as requested to determine the compliance of each component to the requirement

Reporting limit: 50 mg/kg

Requirement 500 mg/kg

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Phthalates

Test Method : With reference to CPSC-CH-C1001-09.4. Analysis was conducted by GC-MS.

<u>Test Item(s)</u>	<u>CAS NO.</u>	<u>1</u>
Benzylbutyl Phthalate (BBP)	85-68-7	ND
Dibutyl Phthalate (DBP)	84-74-2	ND
Bis-(2-ethylhexyl) Phthalate (DEHP)	117-81-7	ND
Diisodecyl Phthalate (DIDP)	26761-40-0	ND
Diisononyl Phthalate (DINP)	28553-12-0	ND
Di-n-octyl Phthalate (DNOP)	117-84-0	ND
Di-n-Hexylphthalate (DnHP)	84-75-3	ND
Diisobutyl phthalate (DIBP)	84-69-5	ND
Dicyclohexyl phthalate (DCHP)	84-61-7	ND
Diethylphthalate (DEP)	84-66-2	ND
Dimethylphthalate (DMP)	131-11-3	ND
Di-n-pentylphthalate (DnPP)	131-18-0	ND
1,2-Benzenedicarboxylic acid, dipentylester, branched and linear (DPP)	84777-06-0	ND
Di-C7-11 branched alkylphthalate (DHNUP)	68515-42-4	ND
1,2-Benzenedicarboxylic acid, dihexyl ester, branched and linear standard (DHP)	68515-50-4	ND
1,2-Benzenedicarboxylic acid, di-C6-8-branched alkyl esters, C7-rich (DIHP)	71888-89-6	ND
Di-isooctyl phthalate (DIOP)	27554-26-3	ND
Diisopentylphthalate (DiPP)	605-50-5	ND
Bis (2-methoxyethyl) phthalate (DMEP)	117-82-8	ND
1,2-Benzenedicarboxylic acid, di-C6-10-alkyl esters or mixed decyl and hexyl and octyl diesters with ≥ 0.3% of dihexyl phthalate; 1,2-Benzenedicarboxylic acid, mixed decyl and hexyl and octyl diesters	68515-51-5 / 68648-93-1	ND
Di-n-propyl phthalate (DPRP)	131-16-8	ND
N-pentyl-isopentyl phthalate (nPiPP)	776297-69-9	ND
Di-iso-hexyl phthalate (DIHxP)	71850-09-4	ND
Sum		ND
Conclusion		PASS

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Notes :

Note: n.d. = not detected

mg/kg = ppm

* = Exceed the limit

= result over 1/2 or 1/3 of client requirement. There is a possibility of failure on one or more components. Retesting on individual component is recommended to determine the compliance of each component to the requirement

Δ = result over 1/2 or 1/3 of client requirement. There is a possibility of failure on one or more components. Retesting on individual component has been carried out as requested to determine the compliance of each component to the requirement

Reporting limit: 50 mg/kg (each)

Requirement

Each 500 mg/kg

Sum 1000 mg/kg

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Polyaromatic hydrocarbons Content (PAH)

Test Method : With reference to AfPS GS 2019:01 PAK. Analysis was conducted by GC-MS.

<u>Test Item(s)</u>	1
Acenaphthene(ANA)	ND
Acenaphthylene(ANY)	ND
Anthracene(ANT)	ND
Benzo(a)anthracene(BaA)	ND
Benzo(a)pyrene(BaP)	ND
Benzo(b)fluoranthene(BbF)	ND
Benzo(e)pyrene(BeP)	ND
Benzo(g,h,i)perylene(BPE)	ND
Benzo(j)fluoranthene(BjF)	ND
Benzo(k)fluoranthene(BkF)	ND
Chrysene(CHR)	ND
Dibenzo(a,h)anthracene(DBA)	ND
Fluoranthene(FLT)	ND
Fluorene(FLU)	ND
Indeno(1,2,3-c,d)pyrene(IPY)	ND
Naphthalene(NAP)	ND
Phenanthrene(PHE)	ND
Pyrene(PYR)	ND
Sum of 18 PAHs	ND
Conclusion	PASS

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Notes :

Note: n.d. = Not detected

mg/kg = ppm

* = Exceeds the limit

= result over 1/2 or 1/3 of client requirement. There is a possibility of failure on one or more components. Retesting on individual component is recommended to determine the compliance of each component to the requirement

Δ = result over 1/2 or 1/3 of client requirement. There is a possibility of failure on one or more components. Retesting on individual component has been carried out as requested to determine the compliance of each component to the requirement

Reporting limit = 0.1 mg/kg (each)

Requirement

	Childcare Article	Others
Benzo[a]anthracene	0.5 mg/kg	1 mg/kg
Benzo[a]pyrene	0.5 mg/kg	1 mg/kg
Benzo[b]fluoranthene	0.5 mg/kg	1 mg/kg
Benzo[e]pyrene	0.5 mg/kg	1 mg/kg
Benzo[j]fluoranthene	0.5 mg/kg	1 mg/kg
Benzo[k]fluoranthene	0.5 mg/kg	1 mg/kg
Chrysene	0.5 mg/kg	1 mg/kg
Dibenzo[a,h]anthracene	0.5 mg/kg	1 mg/kg
Sum of 18 PAH	10 mg/kg	10 mg/kg

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Volatile Organic Compounds (VOCs)

Test Method : With reference to AFIRM RSL 2022 method. Analysis was conducted by headspace GC-MS.

<u>Test Item(s)</u>	<u>CAS NO.</u>	<u>1</u>
Benzene	71-43-2	ND
CarbonDisulphide (CS2)	75-15-0	ND
Ethylbenzene	100-41-4	ND
Toluene	108-88-3	ND
Xylenes (meta-, ortho-, para-)	1330-20-7	ND
Trichloroethylene	79-01-6	ND
Tetrachloroethylene	127-18-4	ND
Cyclohexanone	108-94-1	ND
1,2-Dichloroethane	107-06-2	ND
1,1-Dichloroethene	75-35-4	ND
Chloroform	67-66-3	ND
Carbon tetrachloride	56-23-5	ND
1,1,1-Trichloroethane	71-55-6	ND
1,1,2-Trichloroethane	79-00-5	ND
1,1,1,2-Tetrachloroethane	630-20-6	ND
1,1,2,2-Tetrachloroethane	79-34-5	ND
Pentachloroethane	76-01-7	ND
Sum of VOCs (Except benzene)		ND
Conclusion		PASS

Notes :

Note: n.d. = not detected

mg/kg = ppm

* = Exceed the limit

= result over 1/2 or 1/3 of client requirement. There is a possibility of failure on one or more components. Retesting on individual component is recommended to determine the compliance of each component to the requirement

Δ = result over 1/2 or 1/3 of client requirement. There is a possibility of failure on one or more components. Retesting on individual component has been carried out as requested to determine the compliance of each component to the requirement

Reporting limit

Benzene = 1 mg/kg

Others = 20 mg/kg (each)

Requirement

Benzene 5 mg/kg

Sum of VOCs (except Benzene) 1000 mg/kg

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Total Arsenic Content - All other materials, except Leather

Test Method : With reference to DIN EN 16711-1:2016. Analysis was conducted by ICP-OES or ICP-MS.

<u>Test Item(s)</u>	<u>CAS NO.</u>	<u>1</u>
Arsenic (As)	7440-38-2	ND
Conclusion		PASS

Notes :

Note: n.d.= Not detected

mg/kg = ppm

* = Exceeds the limit

= result over 1/2 or 1/3 of client requirement. There is a possibility of failure on one or more components. Retesting on individual component is recommended to determine the compliance of each component to the requirement

Δ = result over 1/2 or 1/3 of client requirement. There is a possibility of failure on one or more components. Retesting on individual component has been carried out as requested to determine the compliance of each component to the requirement

Reporting limit = 10 mg/kg

Requirement 100 mg/kg

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Total Cadmium Content - All other materials, except Leather

Test Method : With reference to DIN EN 16711-1:2016. Analysis was conducted by ICP-OES or ICP-MS.

<u>Test Item(s)</u>	<u>CAS NO.</u>	<u>1</u>
Cadmium (Cd)	7440-43-9	ND
Conclusion		PASS

Notes :

Note: n.d.= Not detected

mg/kg = ppm

* = Exceeds the limit

= result over 1/2 or 1/3 of client requirement. There is a possibility of failure on one or more components. Retesting on individual component is recommended to determine the compliance of each component to the requirement

Δ = result over 1/2 or 1/3 of client requirement. There is a possibility of failure on one or more components. Retesting on individual component has been carried out as requested to determine the compliance of each component to the requirement

Reporting limit = 5 mg/kg

Requirement 40 mg/kg

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Total Mercury Content - All other materials, except Leather

Test Method : With reference to DIN EN 16711-1:2016. Analysis was conducted by ICP-OES or ICP-MS.

<u>Test Item(s)</u>	<u>CAS NO.</u>	1
Mercury (Hg)	7439-97-6	ND
Conclusion		PASS

Notes :

Note: n.d.= Not detected

mg/kg = ppm

* = Exceeds the limit

= result over 1/2 or 1/3 of client requirement. There is a possibility of failure on one or more components. Retesting on individual component is recommended to determine the compliance of each component to the requirement

Δ = result over 1/2 or 1/3 of client requirement. There is a possibility of failure on one or more components. Retesting on individual component has been carried out as requested to determine the compliance of each component to the requirement

Reporting limit = 0.1 mg/kg

Requirement 0.5 mg/kg

Total Lead Content - Paint and Surface Coating

Test Method : With reference to CPSC-CH-E1003-09.1. Analysis was conducted by ICP-OES or ICP-MS.

<u>Test Item(s)</u>	<u>CAS NO.</u>	1
Lead (Pb)	7439-92-1	ND
Conclusion		PASS

Notes :

Note: n.d.= Not detected

mg/kg = ppm

* = Exceeds the limit

= result over 1/2 or 1/3 of client requirement. There is a possibility of failure on one or more components. Retesting on individual component is recommended to determine the compliance of each component to the requirement

Δ = result over 1/2 or 1/3 of client requirement. There is a possibility of failure on one or more components. Retesting on individual component has been carried out as requested to determine the compliance of each component to the requirement

The result is calculated using the minimum sample weight

Reporting limit = 10 mg/kg

Requirement 90 mg/kg

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Solvents Residuals – N,N-Dimethylformamide (DMFa) – All other materials, except Textile

Test Method : With reference to DIN CEN ISO/TS 16189:2013. Analysis was conducted by GC-MS.

<u>Test Item(s)</u>	<u>CAS NO.</u>	<u>1</u>
N,N-Dimethyl formamide (DMFa)	68-12-2	ND
Conclusion		PASS

Notes :

- Note: n.d. = Not detected
- mg/kg = ppm
- * = Exceed the limit
- # = result over 1/2 or 1/3 of client requirement. There is a possibility of failure on one or more components. Retesting on individual component is recommended to determine the compliance of each component to the requirement
- Δ = result over 1/2 or 1/3 of client requirement. There is a possibility of failure on one or more components. Retesting on individual component has been carried out as requested to determine the compliance of each component to the requirement
- Reporting limit = 50 mg/kg
- Requirement 500 mg/kg

Solvents Residuals - Formamide - All other materials, except Textile

Test Method : With reference to DIN CEN ISO/TS 16189:2013. Analysis was conducted by GC-MS.

<u>Test Item(s)</u>	<u>1</u>
Formamide	ND
Conclusion	PASS

Notes :

- Note: n.d. = Not detected
- mg/kg = ppm
- * = Exceeds the limit
- # = result over 1/2 or 1/3 of client requirement. There is a possibility of failure on one or more components. Retesting on individual component is recommended to determine the compliance of each component to the requirement
- Δ = result over 1/2 or 1/3 of client requirement. There is a possibility of failure on one or more components. Retesting on individual component has been carried out as requested to determine the compliance of each component to the requirement
- Reporting limit = 50 mg/kg
- Requirement 1000 mg/kg

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Solvents Residuals - DMAc & NMP - All other materials, except Textile

Test Method : With reference to DIN CEN ISO/TS 16189:2013. Analysis was conducted by GC-MS.

<u>Test Item(s)</u>	1
N-Methylpyrrolidone (NMP)	ND
N,N-Dimethylacetamide (DMAc)	ND
Conclusion	PASS

Notes :

Note: n.d. = Not detected

mg/kg = ppm

* = Exceeds the limit

= result over 1/2 or 1/3 of client requirement. There is a possibility of failure on one or more components. Retesting on individual component is recommended to determine the compliance of each component to the requirement

Δ = result over 1/2 or 1/3 of client requirement. There is a possibility of failure on one or more components. Retesting on individual component has been carried out as requested to determine the compliance of each component to the requirement

Reporting limit = 50 mg/kg (each)

Requirement

DMAc, NMP 1000 mg/kg (each)

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Organotin- Textiles

Test Method : With reference to EN ISO 22744-1:2020. Analysis was conducted by GC-MS.

<u>Test Item(s)</u>	1
Trioctyltin(TOT)	ND
Trimethyltin(TMT)	ND
Tricyclohexyl tin (TCyT)	ND
Tributyl tin (TBT)	ND
Tri-n-propyltin(TPT)	ND
Triphenyl tin (TPhT)	ND
Monobutyl tin (MBT)	ND
Dioctyl tin (DOT)	ND
Dibutyl tin (DBT)	ND
Conclusion	PASS

Notes :

Note: n.d.= not detected

mg/kg = ppm

* = Exceed the limit

= result over 1/2 or 1/3 of client requirement. There is a possibility of failure on one or more components. Retesting on individual component is recommended to determine the compliance of each component to the requirement

Δ = result over 1/2 or 1/3 of client requirement. There is a possibility of failure on one or more components. Retesting on individual component has been carried out as requested to determine the compliance of each component to the requirement

Reporting limit = 0.1 mg/kg (each)

Requirement

DBT, DOT, MBT, TCyT, TMT, TOT, TPT 1.0 mg/kg (each)

TBT, TPhT 0.5 mg/kg (each)

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Perfluorinated and Polyfluorinated Chemicals (PFCs)

Test Method : With reference to ISO 23702-1: 2018. Analysis was conducted by HPLC-MS, HPLC-MS/MS and GC-MS.

<u>Test Item(s)</u>	<u>CAS NO.</u>	<u>1</u>
PFOS and related substances		--
Perfluorooctane Sulfonate (PFOS)^	1763-23-1	ND
N-ethylperfluoro-1-octanesulfonamide (EtFOSA)	4151-50-2	ND
N-methylperfluoro-1-octanesulfonamide (MeFOSA)	31506-32-8	ND
2-(N-methylperfluoro-1-octanesulfonamido) - ethanol (MeFOSE)	24448-09-7	ND
2-(N-ethylperfluoro-1-octanesulfonamido)-ethanol (EtFOSE)	1691-99-2	ND
Perfluorooctane Sulfonamide (PFOSA)	754-91-6	ND
Sum of PFOS and related substances		ND
PFOA and its salts		--
Perfluorooctanoic acid (PFOA)+	335-67-1	ND
PFOA-related substances		--
1H,1H,2H,2H-Perfluorodecanesulfonic acid (8:2 FTS)	39108-34-4	ND
1H,1H,2H,2H-Perfluoro-1-decanol (8:2 FTOH)	678-39-7	ND
1H,1H,2H,2H-Perfluorodecylacrylate (8:2 FTA)	27905-45-9	ND
1H,1H,2H,2H-Perfluorodecyl methacrylate (8:2 FTMA)	1996-88-9	ND
Ethyl perfluorooctanoate (Et-PFOA)	3108-24-5	ND
Methyl perfluorooctanoate (Me-PFOA)	376-27-2	ND
Sum of PFOA-related substances		ND
Conclusion		PASS

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Notes :

Note: n.d. = Not detected

^ PFOS refer to its salts/derivative including PFOS-K (CAS No.: 2795-39-3) , PFOS-Li (CAS No.: 29457-72-5), PFOS-NH₄ (CAS No.: 29081-56-9), PFOS-NH(OH)₂ (CAS No.: 70225-14-8), PFOS-N(C₂H₅)₄ (CAS No.: 56773-42-3) and POSF (CAS No.: 307-35-7)

+ PFOA refer to its salts including PFOA-Na (CAS No.: 335-95-5), PFOA-K (CAS No.: 2395-00-8), PFOA-Ag (CAS No.: 335-93-3), PFOA-F (CAS No.: 335-66-0) and APFO (CAS No.: 3825-26-1)

* = Exceeds the limit

Reporting limit

PFOS and related substances = 1mg/kg

PFOA and its salts = 0.025 mg/kg

PFOA related substances = 1 mg/kg

Requirement

PFOS and related substances 1 mg/kg (sum)

PFOA and its salts 0.025 mg/kg (sum)

PFOA-related substances 1 mg/kg (sum)

***** End of Report *****

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.